



Self-Trim Candlewick

The Self-Trim line of wick was developed for use in tapers and candlesticks. Our balanced construction is designed to produce a gentle curl that is self-trimming and will not over curl. Fil-Tec's scientifically engineered chemical treatment reduces afterglow, enhances the self-trimming and helps control the curl. The wick's open construction allows for better capillary flow when using heavily scented paraffin, vegetable based and beeswax wax blends. Our Patented construction also delivers a consistent rate of consumption. Fil-Tec Self-Trim wick offers a higher yield than conventional braided wick, which means lower material costs and longer production runs.

WICK & PART NUMBER	FLAME HEIGHT	RATE OF CONSUMPTION	POOL DIAMETER	WICK YIELD
Self –Trim FT 1.875 Part # 54009	1.3 inch 3.3 cm	5.5 grams / hour	1.875 inch 4.8 cm	760 yards / lb. 1532 meters / kg.
Self –Trim FT 2.010 Part # 54277	1.4 inch 3.6 cm	5.05 grams / hour	2.010 inch 5.1 cm	945 yards / lb. 1905 meters / kg.
Self –Trim FT 2.015 Part # 54442	1.3 inch 3.3 cm	5.2 grams / hour	2.015 inch 5.1 cm	772 yards / lb. 1556 meters / kg.
Self –Trim FT 2.023 Part # 54475	1.4 inch 3.6 cm	5.46 grams / hour	2.023 inch 5.1 cm	672 yards / lb. 1355 meters / kg.
Self –Trim FT 2.239 Part # 54423	1.8 inch 4.6 cm	7.03 grams / hour	2.239 inch 5.7 cm	477 yards / lb. 961 meters / kg.
Self –Trim FT 2.297 Part # 54430	1.5 inch 3.8 cm	6.24 grams / hour	2.297 inch 5.8 cm	582 yards / lb. 1175 meters / kg.
Self –Trim FT 2.346 Part # 54354	1.8 inch 4.6 cm	7.0 grams / hour	2.346 inch 6.0 cm	381 yards / lb. 768 meters / kg.
Self –Trim FT 2.589 Part # 54347	1.9 inch 4.8 cm	8.6 grams / hour	2.589 inch 6.6 cm	445 yards / lb. 897 meters / kg.

Our product description is very "user-friendly". The description represents the 2 hour pool diameter in a 140° melt point straight cut paraffin wax. This method allows the user to easily compare wick size and performance. This chart provides the candle maker a starting point for wick selection. Your wick selection will depend on wax blend, color and scent additives.

5/29/2009

FIL-TEC Inc. P.O. Box B Hagerstown, Maryland 21741-1191 USA

Phone: 301-824-6166 Fax: 301-824-1125